



# Acryl 80

**ACRYL 80** is a water based acryl paint for interior, featuring both good resistant of applied film and good vapour diffusion rate.

**ACRYL 80** is suitable for any interior wall where it is required a good quality paint at reasonable price. Good hiding power and coverage, easy to apply, **ACRYL 80** protects the wall against moulds, thanks to a lemon scented fungicide.

**COLOURS:** White and tintosystem colours

## SURFACE

**PREPARATION:** **New walls:** apply one coat of **SAIFSEAL ACRYL 300%** (dilution by water: 300%).

**Old walls:** brush all flaking and dusty old paints, clean carefully and apply one coat of **SAIFSEAL DUR** (dilution 300% by water). On deteriorated dusty plasters: apply one coat of **SAIFSEAL DUR 300%**.

**Old mouldy walls :** first apply one or two coats of " **NO MOULD**". After drying, take out all dusty staff and proceed with one coat of **SAIFSEAL SAN** (mould inhibitor undercoat) .

**APPLICATION:** According to surface absorption, dilute from 20 to 30% by water. Mix the product thoroughly before application. Apply two coats by brush, power or airless spray-gun. Second coat dilution: 20%. Do not apply under + 5° C.. **ACRYL 80** is odourless, any way, keep windows open while the coat is drying.



# Acryl 80

Linea Acryl

<b>&gt;ACRYL 80</b>		N A 02
		REV 0
		05/11/2004
		SPEC. REF. A 02
<b>TECHNICAL DATA</b>		
Binding agent :	Modified acryl resin	
Specific weight:	1,63 kg /l $\pm$ 2%	UNI 8910
pH:	8,5÷9,5	UNI 8311
Viscosity Brookfield:	50000 CPS a 20° C. S. 5 RPM $5 \pm 10\%$	UNI 8490
% Solid weight:	66,8% $\pm$ 2	ISTR 0007
<b>APPLICATION DATA</b>		
Storage Temperature:	From +5°C to +45°C	
Application Temperature:	From +5°C to +40°C	
Shelf life:	Dry and fresh store, packed and sealed 18 months at least.	
Dilution:	20-30% water, according to substrate absorption .	
Drying Time:	1 hours touch dry. Recoatable after 4-6 hours.	
Consumption:	4 - 5 mq/ lt	
Packing:	2,5 lt – 5 l - 10 lt - 15 lt.	

These data are result of scrupulous tests and are showing our most updated knowledge. These data are distributed as information and cannot be proof for a dispute since the application and conservation of the product may change not under our responsibility.