n Saifseal San 300

SAIFSEAL SAN 300 is a specific undercoat for mouldy walls able to treat and prepare the wall for further coatings inhibiting the mould formations. On gypsum or plaster walls or panels, **SAIFSEAL SAN 300** contributes to uniform the absorption thanks to the highly penetrating properties of its binder micromolecules. High penetration consolidating properties, permanent bactericide, mould inhibition effect, low V.O.C (Directive 2004/ 42/C.E. enforced by DL 161 dated 27/3/2006), make **SAIFSEAL SAN 300** environment friendly high tech product.

COLOUR: Transparent

APPLICATION: SAIFSEAL SAN 300, to be dilute by water at 300% (one part of

SAIFSEAL SAN 300 and three parts of water), can be applied on dry gypsum board - fibre cement - plaster. etc... First, if necessary, take out all loosing staff, by iron brushing the surface. Apply one **SAIFSEAL SAN 300** coat. Highly absorbent surfaces may require a second coat. On walls heavily covered by moulds, treat by **NO**

MOULD before applying **SAIFSEAL SAN**.

Allow few hours between applications. Before each application,

mix well the product. Apply by roller or brush.

SAIF s.r.l.VIA ACQUI, 31
15014 CANTALUPO – ALESSANDRIA - ITALY
Tel. (0131) 269207 –269208
Fax (0131) 269200

SISTEMA DI GESTIONE QUALITÀ UNI EN ISO 9001:2000 CERTIFICATO DA CERTIQUALITY

AZIENDA CON

e-mail: <u>saif@saifspa.it</u> <u>www.saifspa.it</u>



| >SAIFSEAL SAN 300 | | N 526 |
|--------------------------|--|----------------|
| | | REV |
| | | 31/01/2007 |
| | | SPEC. REF. 526 |
| TECHNICAL DATA | | |
| Binding agent : | Modified acryl resin | |
| Specific weight: | 1,04 kg /l ± 2% | UNI 8910 |
| рН: | 8,5÷9,5 | UNI 8311 |
| Viscosity Brookfield: | 10÷20 CPS a 20° C. S. 1 RPM 10 ± 10% | UNI 8490 |
| V.O.C. | 39 gr/l | |
| APPLICATION DATA | | |
| Storage Temperature: | From +5°C to +40°C | |
| Application Temperature: | From +5°C to +45°C | |
| Shelf life: | Dry and fresh store, packed and sealed 18 months at least. | |
| Dilution: | Add 300% water | |
| Drying Time: | 2 hours touch dry. Recoatable after 10 hours. | |
| Consumption: | From 0,1 to 0,15 l/mq | |
| Packing: | 0,500 - 5 - | |

These data are result of scrupulous tests and are showing our most updated knowledge. These data are distributed as information and cannot be proof for a dispute since the application and conservation of the product may change not under our responsibility.

AZIENDA CON SISTEMA DI GESTIONE QUALITÀ UNI EN ISO 9001:2000 CERTIFICATO DA CERTIQUALITY **SAIF s.r.l.**VIA ACQUI, 31
15014 CANTALUPO – ALESSANDRIA - ITALY
Tel. (0131) 269207 –269208
Fax (0131) 269200

e-mail: <u>saif@saifspa.it</u> <u>www.saifspa.it</u>