



Saturno

SATURNO is a decorative system for interior applied by stainless steel spatula, that gives to the wall an antique and precious gold, silver or bronze finish look.

Thanks to the particles of different colours, its light pigmentation and light dark effects, **SATURNO** "dress" the wall with a spectacular interior decorative effects.

SATURNO has a great resistance and washability, it keeps its look for long time without aging and, due to its structure, helps hiding surface imperfections of the wall. In case of damages **SATURNO** surface can be easily repaired.

SATURNO creates artistic effects on the wall, it can be added to gold, silver or bronze **REFLECTA DOSES**.

COLOURS: 24 colors available, each one to be tinted by perlescent **REFLECTA DOSE**.

SURFACE PREPARATION: First apply one coat of **SAIFSEAL DUR 300%** and let it dry, then apply one coat of **MICROFOND** diluting at 10 -20% by water, applying it by brush and smoothing the wet surface by using a flat plastic trowel.

APPLICATION: Add to the chosen ℓ 2,5 **SATURNO** color the **REFLECTA DOSE** (gold, silver, bronze). Mix slowly without using mechanicals tools. Apply by stainless steel spatula one coat of **SATURNO**, to cover completely the surface pressing it immediately the soft particles by slight trowel pressure. A non uniform distribution of the particles doesn't compromise the final result. Do not go back with the trowel on already applied **SATURNO** surface unless on areas where there is too much materials, in such a case by almost flat trowel, press the particles once.

One coat can be enough to reach a good effect.

If required, can be reached a real "Granite" effect applying one or two coats of **VARNISH GREEN** by brush on completely dry **SATURNO**.

Clean tools immediately after use, by warm water and soap.



Saturno

>SATURNO		N O 03
		REV 0
		DEL 06/04/2006
		SPEC. REF. O 03
TECHNICAL DATA		
Binding Agent:	Acryl resin	
Specific weight:	1,00 kg /l \pm 2%	UNI 8910
pH:	6÷7	UNI 8311
Viscosity Brookfield:	70000 CPS a 20° C. S. 7 RPM $2 \pm 10\%$	UNI 8490
% Solid by weight:	6% \pm 2	ISTR 0007
APPLICATION DATA		
Storage temperature	From +10°C to +30°C	
Application Temperature:	From +10°C to +40°C	
Shelf life:	Dry and fresh store, packed and sealed 6 months at least.	
Dilution:	Ready to use	
Drying Time:	3 hours touch dry. Recoatable after 8 hours	
Consumption:	from 300 to 400 g/mq	
Packing:	2,5 l	

These data are result of scrupulous tests and are showing our most updated knowledge. These data are distributed as information and cannot be proof for a dispute since the application and conservation of the product may change not under our responsibility.