



Easy to apply, high coverage , excellent resistance to chlorine water, is the best solution to traditional swimming pool walls and floor.

**COLOURS:** Light blue. Other colours available on request.

**Old walls:** carefully take out any loose old coat (sandblasting is suggested) then apply two coats of **SAIFSEAL PLYO**. Surface should be dry and sound.

# Linea Uno



# Uno Pool

Linea Uno

<b>&gt;UNO POOL</b>		N U 02
		REV 0
		05/11/2004
		SPEC. REF. U 02
<b>TECHNICAL DATA</b>		
Binding agent :	chlorinated rubber	
Specific weight:	1,3 kg /l $\pm$ 2%	UNI 8910
pH:		UNI 8311
Viscosity Brookfield:	15000 CPS a 20° C. S. 5 RPM $\pm$ 10%	UNI 8490
% Solid weight:	40,8% $\pm$ 2	ISTR 0007
<b>APPLICATION DATA</b>		
Storage Temperature:	From +5°C to +45°C	
Application Temperature:	From +15°C to +30°C	
Shelf life:	Dry and fresh store, packed and sealed 18 months at least.	
Dilution:	5 -15% synthetic thinner, according to substrate absorption .	
Drying Time:	4 - 5 hours touch dry. Recoatable after 12-24 hours. Wait 6 days before filling the pool by water.	
Consumption:	4 -5 sqmt/lt. two coats	
Packing:	2,5 lt – 15 lt.	

These data are result of scrupulous tests and are showing our most updated knowledge. These data are distributed as information and cannot be proof for a dispute since the application and conservation of the product may change not under our responsibility.