



Uno Satin/3

UNO SATIN has been formulated in order to have a versatile satin paint, scratch resistant and easy to apply. The right place of **UNO SATIN/3**, in terms of quality and performance, is in between a traditional good acryl paint and a modern water based enamel. This silky finish coat is the answer for protection of interior plastered walls, gypsum boards or wood. **UNO SATIN/3**, due to its high adhesion power, and its resistance to water and scratches, can be applied on smooth surfaces and cleaned by water or mild detergents. **UNO SATIN/3** new formula, due to permanent antibacterial additive grants high resistance to mould formation; It is an ideal solution for public places and as undercoat for "**RIFLESSI**", instead of Green Coat.

COLOURS: Standard white.
Full range of light colours by tintosystem.

SURFACE PREPARATION: **New walls:** apply one coat of **SAIFSEAL DUR** (dilution 300% by water).
Old walls: brush the wall to take out all flaking old paints. Apply one coat of **SAIFSEAL DUR** or, on old bad walls.
Mouldy walls: apply at least one coat of "**NO MOULD**", until the mould is destroyed. Clean carefully taking out all dusty stuff, proceed as above.

APPLICATION: Dilution 15- 20% by water as first coat and 10% second coat. Mix the product before application, let first coat dry for at least 6 hours.
Application tools: brush , roller, spray-gun.
Do not apply under +10°C. Plaster should be perfectly dry and cured. **UNO SATIN/3** is odourless and can be apply in schools, hospitals, public places without special precautions. Clean tools immediately after application by warm water.



Uno Satin/3

>UNO SATIN/3		N U 04
		REV 0
		DEL 05/11/2004
		SPEC. REF. U 04
TECHNICAL DATA		
Binding agent :	Modified acryl resin	
Specific weight:	1,32 kg /l \pm 2%	UNI 8910
pH:	8,5÷9,5	UNI 8311
Viscosity Brookfield:	11000 CPS a 20° C. S. 5 RPM $5 \pm 10\%$	UNI 8490
% Solid weight:	56,8 \pm 2	ISTR 0007
APPLICATION DATA		
Storage Temperature:	From +5°C to +40°C	
Application Temperature:	From +5°C to +40°C	
Shelf life:	Dry and fresh store, packed and sealed 18 months at least.	
Dilution:	50-10% water, according to substrate absorption .	
Drying Time:	1 hours touch dry. Recoatable after 4-6 hours.	
Consumption:	from 6 to 8 kg/mq two coats.	
Packing:	0,750 l - 2,5 l – 15 l	

These data are result of scrupulous tests and are showing our most updated knowledge. These data are distributed as information and cannot be proof for a dispute since the application and conservation of the product may change not under our responsibility.