

Interior rolled coating based on quartz and calcium carbonates, giving a finishing fine pattern "orange peel" type.

Vega Bl

STANDARD COLOURS:	"I RESTAURI" colour card including 132 colours
SURFACE PREPARATION:	New walls: apply one or two coats of coloured " SAIFSEAL COAT QUARTZ" ; (very absorbent walls require a previous coat of "SAIFSEAL BETON 300%"). Old walls: take out all flaking, old paints by iron brush, clean the wall and apply one coat of "SAIFSEAL DUR" . Proceed with application of SAIFSEAL COAT QUARTZ. Old mouldy walls : first apply one or two coats of " NO MOULD". After drying, take out all dusty staff and proceed with one coat of SAIFSEAL SAN (mould inhibitor undercoat)
APPLICATION:	Ready to use, stir before application. Spread the paste on the surface using a steel trowel, keeping uniform thickness, or apply directly by sponge roller, fine grade or medium grade. In order to reach a smoother patterns, without tips, add one glass of water each 25 kg drum. First roll the product horizontally, then vertically; repeat until the thickness and pattern are uniform. Final operation will be always vertical, keeping a uniform roller pressure. Application by spray needs un upper gun, pressure atm 2.5 and nozzle 5mm. Higher pressure reduces the size of the patters. Solvent free product, do not require special precautions, just keep the windows open during application. Deep drying time: 72 hours . Tools cleaning: warm water.

AZIENDA CON SISTEMA DI GESTIONE QUALITÀ UNI EN ISO 9001:2000 CERTIFICATO DA CERTIQUALITY

e-mail: <u>saif@saifspa.it</u> <u>www.saifspa.it</u>



Vega Bl

> VEGA BL	N V 03		
		REV 0	
		05/11/2004	
		SPEC. REF. V 03	
TECHNICAL DATA			
Binding agent :	Styro-acryl		
Specific weight:	<b>1,8</b> kg /l ± 2%	UNI 8910	
pH:	8,5÷9,5	UNI 8311	
Viscosity Brookfield:	<b>170.000</b> CPS a 20° C RPM 2 S 6 ±10%	UNI 8490	
% Solid weight:	<b>74,3</b> ± 2	ISTR 0007	
APPLICATION DATA			
Storage Temperature:	From +5°C to +45°C		
Application Temperature:	From + 10° a + 35° C.		
Shelf life:	dry and fresh store, 12 months; temperature from +5°		
	to 45° C.		
Dilution:	ready to use.		
Drying Time:	3 hours touch dry, 72 hours completely dry.		
Consumption: from 0.8 to 1.5 kg / mq., according to		ding to required	
	pattern.		
Packing:	Packing: 5 kg – 25 kg		

These data are result of scrupulous tests and are showing our most updated knowledge. These data are distributed as information and cannot be proof for a dispute since the application and conservation of the product may change not under our responsibility.

AZIENDA CON SISTEMA DI GESTIONE QUALITÀ UNI EN ISO 9001:2000 CERTIFICATO DA CERTIQUALITY **SAIF s.r.l.** VIA ACQUI, 31 15014 CANTALUPO – ALESSANDRIA - ITALY Tel. (0131) 269207 –269208 Fax (0131) 269200

e-mail: <u>saif@saifspa.it</u> <u>www.saifspa.it</u>